



# LPS 3<sup>®</sup>

## PREMIER RUST INHIBITOR



Qualified to: BMS 3-23 G Type II, TN  
 A.007.10138 Type I Grade 2  
 DMS 2150, Lockheed G39.2004  
 Conforms to: Mil-PRF-16173E Grade 2  
 ASTM F-945, PWA 36604



Category Code H2  
 Registration No.:  
 # 129027 Aerosol  
 # 059849 Bulk

### PACKAGES

#### Net Fill

11 oz. (312 grams) aerosol  
 1 gal. (3.78 liters)  
 18.9Ltr

#### Part No.

00316  
 03128  
 00305

### APPLICATIONS

- Aircraft Fuselages
- Battery Terminals
- Cables, Chains, & Pulleys
- Cargo Sections
- Elevators
- Metal Parts
- Offshore Drilling Equipment
- Outdoor Electrical Connections
- Outdoor Equipment & Tools
- Overseas Storage or Shipments
- Pumps & Hose Assemblies
- Interior Sections of Vehicle Doors



### PROPERTIES

Appearance/Physical State:  
 Opaque brown liquid  
 Dielectric Strength (ASTM D-877):  
 19.5 kv  
 Flash Point: (TCC)  
 100°F (40°C) minimum  
 HMIS: 1, 2, 0  
 Humidity Cabinet Test (ASTM D  
 1748): No rust on 1029 steel panels  
 after 30 days

Pour Point: 0°F (- 18°C)  
 Propellant: Carbon Dioxide  
 Salt Spray Cabinet Test (ASTM D117):  
 No corrosion on 2024-T3 alumi-  
 num panels after 1500 hours  
 Specific Gravity (water=1):  
 0.82 – 0.86  
 Typical Dried Film Thickness:  
 50 – 100 microns (2 - 4 mils)  
 Viscosity at 25°C: 200 – 600 cps

MATERIAL SAFETY DATA SHEETS AVAILABLE UPON REQUEST OR VISIT OUR WEB SITE :[WWW.LPSLABS.COM](http://WWW.LPSLABS.COM)

LPS Laboratories • An Illinois Tool Works Company

P.O. Box 105052 • 4647 Hugh Howell Road • Tucker, GA 30085-5052 • TEL: (800) 241-8334 or (770) 243-8800 • FAX: (800) 543-1563 or (770) 243-8899

Internet Web Site: [www.lpslabs.com](http://www.lpslabs.com)

©2006 LPS Laboratories • LPS<sup>®</sup> is a registered trademark of Illinois Tool Works • Printed in U.S.A. • All Rights Reserved • Form #2015 • Rev. 7/2007