



### OKS 250

#### White Allround Paste, metal-free



#### Description

High-temperature paste on ceramic basis for lubricating heavily loaded sliding surfaces.

#### Applications

- Lubrication of highly stressed sliding surfaces, especially at low slip speeds or with oscillating movements, for example with screwed, mating or bayonet connections made of high-alloy steel or non-ferrous metals
- Surface separation of temperature-stressed threaded connections, for example at combustion engines and turbines
- Corrosion protection at screws, pins, bolts, flanges, spindles and fits
- For stainless-steel connections

#### Advantages and benefits

- Economic product solution for users who previously used a wide variety of pastes
- Resistant to hot and cold water and also to most acids and lyes
- Excellent corrosion protection
- Contains Mo<sub>x</sub>-Active for increased performance
- Metal-free
- Also available as spray version OKS 2501
- NSF H2 registered

#### Branches

- Chemical industry
- Maintenance and servicing
- Iron and steel industry
- Logistics
- Shipbuilding and marine technology
- Paper and packaging industry
- Plant and machine (tool) engineering
- Rail vehicle technology
- Municipal services
- Catering equipment and food processing technology
- Rubber and plastic processing
- Glass and foundry industry



## PRODUCT INFORMATION

### OKS 250

### White Allround Paste, metal-free

#### Application tips

To achieve optimal adhesion remove soiling as well as other lubricants from the thread and sliding surfaces. Use a brush, spatula or similar to apply sufficient OKS 250 to the head or nut contact surface and to the thread. Spray on evenly OKS 2501 spray. The paste will also act as a sealant. Caution: Do not use paste instead of grease and mix only with suitable lubricants.

#### Packaging

- 8 ml Tube
- 80 ml Tube
- 250 g Brush tin
- 1 kg Can
- 5 kg Hobbock
- 25 kg Hobbock

#### Technical Data

	Standard	Conditions	Unit	Value
<b>Main components</b>				
base oil				synthetic oil mixture
thickener				polycarbamide
solid lubricants				white solid lubricants
additives				Mo <sub>x</sub> -Active
<b>Application related technical data</b>				
viscosity at (40°C)			mm <sup>2</sup> /s	360
drop point	DIN ISO 2176		°C	without
unworked penetration	DIN ISO 2137	no shear stress	0.1 mm	280-320
lower operating temperature			°C	-40
upper operating temperature		lubrication	°C	200
upper operating temperature		separation	°C	1,400
colour				white
density (at 20°C)	DIN EN ISO 3838		g/cm <sup>3</sup>	1.25
salt spray test	DIN 50 021	layer thickness 60µm	h	> 500
four-ball test rig welding load	DIN 51 350-4		N	3,600
thread friction coefficient (µ total)	DIN EN ISO 16 047	screw ISO 4017 M10x55-8.8 black-oxide, nut ISO 4032 M10-10 black-oxide		0.12
thread friction coefficient (µ total)	DIN EN ISO 16 047	Screw ISO 4017 A2 M10x55-70, Nut ISO 4032 A2 M10-70		0.15
breakaway torque	DIN 267-27	M10 A2, 40 Nm, 400°C, 100h	Nm	< 2.7 x tightening torque
press-fit test	draft DIN 51 833		µ	0.10, no chatter
<b>Properties and approvals</b>				
approval for food processing technology				NSF H2, Reg.-Nr. 131379

#### OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47  
 82216 Maisach  
 Phone: +49 (0) 8142 3051 - 500  
 info@oks-germany.com  
 www.oks-germany.com



The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark  
**Safety data sheet** for industrial and commercial users is available for downloading under [www.oks-germany.com](http://www.oks-germany.com). Our Customer and Technical service will be pleased to help should you have any further questions.