

	VITAL TECHNICAL SDN. BHD.	 	
	Technical Data Sheet		
	VT-127 Crack Filler		

Issuance date: 31/03/08

Revision date: 17/11/20

Revision No.: 20-02

Product Specification:

Solid content	: 75.0 – 77.0 %
Specific gravity	: 1.80 – 1.82
Working time	: 10 – 20 minutes
Max. operating temperature	: 80 °C
Application temperature range	: 5 °C – 40 °C
Drying time	: 5 – 10 minutes per mm
Color	: White
Features	: Virtually non-shrinking
	: Paintable
	: Easy clean up
Applicable Tests / Standards	: RoSH Directive 2011/65/EU
Shelf life	: 24 months
Packaging	

Product Code	Content	Inner Box	Carton
VT-127	290 g tube	12	72



(Scan to learn how to use)



Visit product page:

<http://vitaltechnical.com/product/vt-127-crack-filler>

Product Description:

An easy-to-use multi-purpose filler specially formulated to fill cracks and gaps in a single application. It has virtually no shrinkage and is smooth and durable. It is paintable with oil and water-based paints.

Applications:

- Filling cracks and holes on surfaces without any structural movements (walls, ceilings, doors, windows, etc.).
- Can be used outdoor if painted over.

Directions:

1. Surfaces must be clean, dry and free of dirt, grease, oil or water.
2. Squeeze tube and push filler into crack or gap, then smooth off the surface with a spatula or scraper.
3. Allow 2 – 3 hours to set in 2 mm applications. The filler can be sanded after drying.
4. Wet filler can be cleaned with wet cloth.
5. Replace cap after use and store in a cool and dry place.

Caution:

Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.

Storage:

- Store in a dry and cool place with temperature below 30 °C.
- Use within 24 months from date of production.

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.